

# DATA SHEET

## **Black Viton® Rubber**



**Unit 21 Priory Industrial Park  
Airspeed Road  
Christchurch  
Dorset  
BH23 4HD**

**Tel: 01425 278011**

**Fax: 01425 278012**

[www.deltarubber.co.uk](http://www.deltarubber.co.uk)

[deltasales@deltarubber.co.uk](mailto:deltasales@deltarubber.co.uk)

### Technical Information

Material:	FKM Fluoroelastomer
Application:	High Chemical, oil, fuel, Resistant
Thickness:	0.5, 1.0, 1.5, 2, 3, 4, 5, 6, 8, 10mm
Colour:	Black
Cloth/Plate Finish:	Plate
Density [specific gravity]:	1.95 g/cm <sup>3</sup>
Hardness [Degrees Shore A]:	70° ± 5°
Tensile Strength [Mpa]:	4.9 min
Elongation at break :	200 %
Minimum Temperature :	-20°C
Maximum temperature:	+300°C
Compression Set :	62% (70°C for 22 hours)
Tear resistance (kg/cm):	20

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any particular application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable, but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied.



Certificate No: GB08/75575

This product is REACH, RoHS, PAH & CE Compliant.